

DURAFIDE® 6165A4

PPS-(GF+MD)65

Polyplastics

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	130	MPa	ISO 527
Strain at break	1.1	%	ISO 527
Flexural modulus, 23°C	19800	MPa	ISO 178
Flexural strength	205	MPa	ISO 178
Charpy notched impact strength, +23°C	6	kJ/m ²	ISO 179/1eA
Rockwell hardness	M 105	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	270	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	10	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	30	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Yellow Card available	yes	-	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Relative permittivity, 1MHz	5.8	-	IEC 62631-2-1
Dissipation factor, 1MHz	20	E-4	IEC 62631-2-1
Volume resistivity	8E13	Ohm*m	IEC 62631-3-1
Electric strength	14	kV/mm	IEC 60243-1
Comparative tracking index	200	-	IEC 60112
ASTM Data			
Arc Resistance	162	s	ASTM D 495

Other properties	Value	Unit	Test Standard
Density	1980	kg/m ³	ISO 1183

Characteristics**Regional Availability**

Asia Pacific