

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Strength	110	MPa	ISO 527
Strain at break	0.8	%	ISO 527
Flexural modulus, 23°C	19500	MPa	ISO 178
Charpy impact strength, +23°C	15	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	8	kJ/m ²	ISO 179/1eA
Rockwell hardness	R 122	-	ISO 2039-2

Thermal properties	Value	Unit	Test Standard
ISO Data			
Melting temperature, 10°C/min	278	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	260	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	20	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	28	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-

Electrical properties	Value	Unit	Test Standard
ISO Data			
Volume resistivity	1000000	Ohm*m	IEC 62631-3-1
Electric strength	6	kV/mm	IEC 60243-1

Other properties	Value	Unit	Test Standard
Density	1860	kg/m ³	ISO 1183

Characteristics

Delivery form

Black

Special Characteristics

Anti-static

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa