

RTP 1389

PPS-CF50

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Mold Shrinkage, MD	0.0005	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	44820	MPa	ASTM D 638
Tensile Strength	145	MPa	ASTM D 638
Flexural Modulus	35160	MPa	ASTM D 790
Flexural Strength	255	MPa	ASTM D 790
Izod Impact notched, 1/8 in	42.7	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	268	°C	ASTM D 648
Electrical properties			
ASTM Data			
Volume Resistivity	100000	Ohm*cm	ASTM D 257
Other properties			
Density	1510	kg/m ³	ASTM D 792
Moisture Content	0.04	%	-
Processing Recommendation Injection Molding			
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	6	h	-
Melt temperature	307 - 329	°C	-
Mold temperature	135 - 177	°C	-
Injection pressure	68.9 - 103	MPa	-

Characteristics**Processing**

Injection Molding

Regional Availability

North America, Europe, Asia Pacific