

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.3	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	15500	MPa	ISO 527
Stress at break	200	MPa	ISO 527
Strain at break	1.8	%	ISO 527
Flexural modulus, 23°C	13800	MPa	ISO 178
Charpy impact strength, +23°C	55	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 179/1eA
Rockwell hardness	M122	-	ISO 2039-2
<b>ASTM Data</b>			
Taber Abrasion Resistance	50	mg/1000 cycles	ASTM D 1044
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	280	°C	ISO 11357-1/-3
Glass transition temperature, 10°C/min	90	°C	ISO 11357-1/-2
Temp. of deflection under load, 1.80 MPa	270	°C	ISO 75-1/-2
Burning behav. at 1.5 mm nom. thickn.	V-0	class	IEC 60695-11-10
Thickness tested	1.6	mm	-
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.4	mm	-
Oxygen index	50	%	ISO 4589-1/-2
<b>Electrical properties</b>			
<b>ISO Data</b>			
Relative permittivity, 1MHz	4.2	-	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Electric strength	24	kV/mm	IEC 60243-1
Comparative tracking index	170	-	IEC 60112
<b>Other properties</b>			
Humidity absorption	0.02	%	Sim. to ISO 62
Density	1660	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Pre-drying - Temperature	130 - 140	°C	-
Pre-drying - Time	3 - 4	h	-
Melt temperature	320 - 340	°C	-
Mold temperature	120 - 150	°C	-
Zone 1	300 - 340	°C	-
Nozzle temperature	320 - 340	°C	-
Screw speed	50 - 120	rpm	-
Injection pressure	50 - 100	MPa	-
Holding pressure	30 - 70	MPa	-
Maximum residence time	10	min	-

## Characteristics

### Delivery form

Natural Color

### Chemical Resistance

General Chemical Resistance

**Special Characteristics**

Flame retardant, Heat stabilized or stable to heat

**Regional Availability**

Europe