

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.6	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.012	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Modulus	1000	MPa	ASTM D 638
Tensile Strength at Yield	26	MPa	ASTM D 638
Tensile Strength at Break	20	MPa	ASTM D 638
Flexural Modulus	1100	MPa	ASTM D 790
Flexural Strength	31	MPa	ASTM D 790
Rockwell Hardness	R 70	-	ASTM D 785

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	83	°C	ASTM D 648
DTUL @ 264 psi	68	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion

Regional Availability

North America

Features

Copolymer