

**ADMER™ AT2717E**

PP

Mitsui Chemicals Europe GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	5.5	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	22	MPa	ASTM D 638
Tensile Strength at Break	26	MPa	ASTM D 638
Elongation at Break	500	%	ASTM D 638
Shore D Hardness	63	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Vicat Temperature	142	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Blown Film Extrusion, Film Extrusion

**Delivery form**

Pellets

**Certifications**

Food contact, Food approval 10/2011, Food approval FDA 21 CFR

**Regional Availability**

Europe