

ADMER™ AT2747E

PP

Mitsui Chemicals Europe GmbH

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238
Temperature	190	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	20	MPa	ASTM D 638
Tensile Strength at Break	22	MPa	ASTM D 638
Elongation at Break	300	%	ASTM D 638
Shore D Hardness	63	-	ASTM D 2240

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Vicat Temperature	146	°C	ASTM D 1525

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Other Extrusion, Coating

Features

Good Adhesion, Thermal Stability, Copolymer

Delivery form

Pellets

Regional Availability

Europe