

**Adstif HA622M**

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	40	MPa	ISO 527
Stress at break	28	MPa	ISO 527
Flexural modulus, 23°C	2200	MPa	ISO 178

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	130	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Film Extrusion

**Certifications**

Food contact

**Special Characteristics**

Heat stabilized or stable to heat

**Applications**

Packaging

**Features**

Barrier Properties, High Crystallinity, Nucleated, Homopolymer

**Regional Availability**

Europe, Near East/Africa