

Adstif HA802H

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	2.3	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	37	MPa	ASTM D 638
Elongation at Yield	8	%	ASTM D 638
Izod Impact notched, 1/8 in	53	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	104	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Film Extrusion, Thermoforming

Delivery form

Pellets

Special Characteristics

Heat stabilized or stable to heat

Features

Homopolymer

Certifications

Food contact, Food approval 1935/2004/EC, Food approval 10/2011, Food approval FDA 21 CFR

Regional Availability

North America