

**Adstif HA1152**

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	25	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	2000	MPa	ISO 527
Yield stress	40	MPa	ISO 527
Yield strain	6	%	ISO 527
Strain at break	15	%	ISO 527
Charpy impact strength, +23°C	60	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	2	kJ/m <sup>2</sup>	ISO 179/1eA
Ball indentation hardness	93	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	110	°C	ISO 75-1/-2
Vicat softening temperature, A	158	°C	ISO 306
Vicat softening temperature, B	104	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Injection Molding

**Applications**

Packaging

**Features**

High Crystallinity, Homopolymer

**Regional Availability**

Europe, Near East/Africa