

**Adsyl 5 C 97 F**

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	5.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	132	°C	ISO 11357-1/-3
Temp. of deflection under load, 0.45 MPa	62	°C	ISO 75-1/-2
Vicat softening temperature, A	107	°C	ISO 306

Optical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Gloss	87	-	ASTM D 2457
Haze	1	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Processing**

Film Extrusion

**Additives**

Antiblocking agent

**Certifications**

Food contact

**Applications**

Packaging

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa