

Adsyl 7415 XCP

PP

LyondellBasell Industries

Processing/Physical Characteristics

	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	0.9	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties

	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	21	MPa	ASTM D 638
Elongation at Yield	14	%	ASTM D 638

Thermal properties

	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	70	°C	ASTM D 648

Other properties

	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Characteristics**Processing**

Blown Film Extrusion

Delivery form

Pellets, Natural Color

Features

Heat Sealable

Certifications

Food contact

Applications

Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa