

Product Texts

Base Polymer	Polypropylene Copolymer
Filler/Additive System	hygienic material
Colour	white, similar to RAL 9003
Special Features	antibacterial acc. to ISO 22196:2011, permanent antibacterial, anti-microbial, contain no nanosilver, impact modified
Market Segment	packaging, Personal care, household goods, Furniture, building and construction
Application Area	injection moulded parts
Typical Applications	sanitary articles, hygiene products, kitchen ware, functional components, housings, handles, containers, caps / closures

Processing/Physical Characteristics

	Value	Unit	Test Standard
ISO Data			
^[C] Melt volume-flow rate, MVR	40	cm ³ /10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

[C]: CAMPUS

Mechanical properties

	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	950	MPa	ISO 527
^[C] Yield stress	20	MPa	ISO 527
^[C] Yield strain	5.5	%	ISO 527
^[C] Charpy impact strength, +23°C	N	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	14	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Thermal properties

	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	50	°C	ISO 75-1/-2
^[C] Vicat softening temperature, B	60	°C	ISO 306

[C]: CAMPUS

Other properties

	Value	Unit	Test Standard
^[C] Density	1000	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics**Processing**

Injection Molding

Features

Copolymer

Delivery form

White

Applications

Building Construction, Packaging

Special Characteristics

High impact or impact modified

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Other text information**Injection molding**

Pre-Drying Conditions

in a dry air (dessiccant) dryer 80-100 °C
for 2-3 h

in an air circulating dryer 80-100 °C
for 2-4 h

max. moisture content <0,10 %

Processing Injection Moulding melt temperature 200-270 °C

mould temperature 20-70 °C

Storage

dry, protected from light
tightly sealed