

**Amppleo 1020GA**

PP

Braskem

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	2	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield	38	MPa	ASTM D 638
Elongation at Break	23	%	ASTM D 638
Izod Impact notched, 1/8 in	30	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
DTUL @ 66 psi	117	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ASTM D 792

**Characteristics****Processing**

Pipe/Tube Extrusion, Profile Extrusion, Sheet Extrusion, Thermoforming

**Regional Availability**

North America, Europe, South and Central America

**Features**

Foamable, Melt Strength, Homopolymer