

BC918CF

PP

Borealis A/S

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	3	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1400	MPa	ISO 178
Charpy notched impact strength, +23°C	35	kJ/m ²	ISO 179/1eA
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	168	°C	ISO 11357-1/-3
Optical properties			
ASTM Data			
Gloss	95	-	ASTM D 2457
Haze	4	%	ASTM D 1003
Film Properties			
ISO Data			
Tensile Modulus, parallel	1150	MPa	ISO 527-3
Tensile Modulus, normal	980	MPa	ISO 527-3
Maximum strain, parallel	570	%	ISO 527-3
Maximum strain, normal	530	%	ISO 527-3
Type of extrusion	blown	-	-
Thickness of specimen	0.05	mm	-

Characteristics**Processing**

Blown Film Extrusion, Film Extrusion, Thermoforming

Features

Heat Sealable, High Crystallinity, High Gloss, Copolymer

Certifications

Food contact

Applications

Packaging

Regional Availability

Europe