

**BE170CF**

PP

Borealis A/S

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	13	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Charpy notched impact strength, +23°C	8	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	80	°C	ISO 75-1/-2
<b>Other properties</b>			
Density	905	kg/m <sup>3</sup>	ISO 1183
<b>Processing Recommendation Injection Molding</b>			
Melt temperature	230 - 260	°C	-
Mold temperature	10 - 30	°C	-
Holding pressure	20 - 50	MPa	-

**Characteristics****Processing**

Injection Molding, Film Extrusion

**Special Characteristics**

High impact or impact modified

**Features**

Low Gel, Low Odor, Copolymer

**Certifications**

Food contact

**Applications**

Packaging

**Regional Availability**

Europe