

BI492

PP

Hanwha TotalEnergies Petrochemical co. Ltd.

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	8	g/10min	ASTM D 1238
Mold Shrinkage, MD	0.016	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Yield	32.4	MPa	ASTM D 638
Elongation at Break	50	%	ASTM D 638
Flexural Modulus	1766	MPa	ASTM D 790
Rockwell Hardness	R 99	-	ASTM D 785
Izod Impact notched, 1/8 in	78.5	J/m	ASTM D 256
Izod Impact notched, Low-Temperature Temperature	39.2 -30	J/m °C	ASTM D 256 -

Thermal properties	Value	Unit	Test Standard
ASTM Data			
DTUL @ 66 psi	130	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	910	kg/m ³	ASTM D 792

Characteristics**Special Characteristics**

Heat stabilized or stable to heat

Applications

Automotive

Chemical Resistance

General Chemical Resistance

Regional Availability

Asia Pacific