

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>4.5</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Yield stress	<b>32</b>	MPa	ISO 527
Yield strain	<b>4</b>	%	ISO 527
Flexural modulus, 23°C	<b>1700</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>8</b>	kJ/m <sup>2</sup>	ISO 179/1eA

**Characteristics**

**Processing**

Injection Molding

**Features**

Thermal Stability, Copolymer

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa