

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2.8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Flexural modulus, 23°C	1350	MPa	ISO 178
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	164	°C	ISO 11357-1/-3

Characteristics**Processing**

Injection Molding, Casting, Thermoforming

Features

Low Odor, Homopolymer

Certifications

Medical Grade

Applications

Medical

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa