

**Product Texts**

LNP LUBRICOMP DFL32 compound is based on Polycarbonate (PC) resin containing 10% glass fiber and 15% PTFE. Added features of this grade include: Wear Resistant.

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Molding shrinkage, parallel	0.2	%	ISO 294-4, 2577
Molding shrinkage, normal	0.7	%	ISO 294-4, 2577
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.2	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.7	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	4100	MPa	ISO 527
Stress at break	71	MPa	ISO 527
Strain at break	2.8	%	ISO 527
Flexural modulus	4170	MPa	ISO 178
Flexural strength	114	MPa	ISO 178
Izod impact strength, +23°C, 4mm	34	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	10	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Modulus	4350	MPa	ASTM D 638
Tensile Strength at Break	73	MPa	ASTM D 638
Elongation at Break	3.1	%	ASTM D 638
Flexural Modulus	4350	MPa	ASTM D 790
Flexural Strength	123	MPa	ASTM D 790
Izod Impact notched, 1/8 in	90	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	534	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	140	°C	ISO 75-1/-2
<b>ASTM Data</b>			
DTUL @ 264 psi	141	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Humidity absorption	0.17	%	Sim. to ISO 62
Water Absorption, 24hr	0.11	%	ASTM D 570
Density	1370	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	305 - 325	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	295 - 305	°C	-
Zone 2	310 - 320	°C	-
Zone 3	320 - 330	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

**Characteristics****Processing**

Injection Molding

**Regional Availability**

North America