

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	3.8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Flexural modulus, 23°C	330	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	149	°C	ISO 11357-1/-3

### Characteristics

#### Processing

Blown Film Extrusion, Film Extrusion

#### Special Characteristics

High impact or impact modified, Sterilizable, Steam sterilization

#### Features

Barrier Properties, Copolymer, Random Copolymer

#### Certifications

Medical Grade, Device Master File

#### Applications

Medical, Packaging

#### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa