

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	<b>70</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	<b>1150</b>	MPa	ISO 527
Yield stress	<b>29</b>	MPa	ISO 527
Yield strain	<b>12</b>	%	ISO 527
Flexural modulus, 23°C	<b>1050</b>	MPa	ISO 178
Charpy notched impact strength, +23°C	<b>4.5</b>	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 0.45 MPa	<b>75</b>	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	<b>905</b>	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Melt temperature	<b>210 - 260</b>	°C	-
Mold temperature	<b>15 - 40</b>	°C	-
Holding pressure	<b>20 - 50</b>	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

Transparent

**Features**

High Crystallinity, Low Odor, Nucleated, Copolymer, Random Copolymer

**Certifications**

Food contact

**Applications**

Packaging

**Regional Availability**

Europe