

BRETENE PP

PP

Breplast S.p.A.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	9.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Strain at break	26	%	ISO 527
Flexural modulus, 23°C	950	MPa	ISO 178
Thermal properties			
ISO Data			
Vicat softening temperature, A	130	°C	ISO 306
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics**Certifications**

Recycled Resin Content

Regional Availability

Europe