

Product Texts

CirculenRecover PP189P Grey contains at least 85% of recycled material.

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	15	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	800	MPa	ISO 527
Tensile Strength	19	MPa	ISO 527
Strain at break	50	%	ISO 527
Charpy notched impact strength, +23°C	30	kJ/m ²	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	918	kg/m ³	ISO 1183
Bulk density	560	kg/m ³	-

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

High impact or impact modified

Features

Copolymer, Impact Copolymer

Certifications

Recycled Resin Content

Applications

General Purpose, Packaging

Regional Availability

Europe