

**COMP 5410 M1**

PP

Exipnos GmbH

<b>Processing/Physical Characteristics</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	<b>20</b>	g/10min	ISO 1133
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
Molding shrinkage, parallel	<b>1.4</b>	%	ISO 294-4, 2577

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	<b>1800</b>	MPa	ISO 527
Yield stress	<b>20</b>	MPa	ISO 527
Yield strain	<b>5</b>	%	ISO 527
Izod notched impact strength, +23°C	<b>12</b>	kJ/m <sup>2</sup>	ISO 180/1A
Izod notched impact strength	<b>7</b>	kJ/m <sup>2</sup>	ISO 180/1A
Temperature	<b>-20</b>	°C	-

<b>Thermal properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Vicat softening temperature, B	<b>75</b>	°C	ISO 306

<b>Other properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
Density	<b>950</b>	kg/m <sup>3</sup>	ISO 1183

**Characteristics****Special Characteristics**

U.V. stabilized or stable to weather

**Regional Availability**

Europe

**Features**

Scratch Resistant