

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	2536	MPa	ISO 527
^[C] Stress at break	15.4	MPa	ISO 527
^[C] Strain at break	5.51	%	ISO 527
^[C] Charpy impact strength, +23°C	20.6	kJ/m ²	ISO 179/1eU
^[C] Charpy notched impact strength, +23°C	1.5	kJ/m ²	ISO 179/1eA

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	1390	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Special Characteristics

U.V. stabilized or stable to weather