

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	<b>0.4</b>	g/10min	ASTM D 1238
Temperature	<b>230</b>	°C	-
Load	<b>2.16</b>	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	<b>25.2</b>	MPa	ASTM D 638
Elongation at Yield	<b>11</b>	%	ASTM D 638
Izod Impact notched, 1/8 in	<b>N</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>81</b>	°C	ASTM D 648
<b>Other properties</b>			
Density	<b>900</b>	kg/m <sup>3</sup>	ASTM D 792

**Characteristics**

**Processing**

Sheet Extrusion

**Delivery form**

Natural Color

**Special Characteristics**

High impact or impact modified

**Features**

Ductile, Copolymer, Impact Copolymer

**Certifications**

US Pharmacopeia Class VI Approved

**Regional Availability**

North America, Europe, Asia Pacific, South and Central America, Near East/Africa