

**Product Texts**

LNP LUBRICOMP DFP32 compound is based on Polycarbonate (PC) resin containing 10% glass fiber, 15% PTFE/silicone. Added features of this grade include: Wear Resistant.

UL Yellow Card Link [E121562-101344538](https://www.ul.com/yellow-card/E121562-101344538)

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Mold Shrinkage, MD	0.6	mm/mm	ASTM D 955
Mold Shrinkage, TD	0.7	mm/mm	ASTM D 955

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	4170	MPa	ISO 527
Stress at break	71	MPa	ISO 527
Strain at break	3.4	%	ISO 527
Flexural modulus	3990	MPa	ISO 178
Flexural strength	121	MPa	ISO 178
Izod impact strength, +23°C, 4mm	37	kJ/m <sup>2</sup>	ISO 180/1U
Izod notched impact strength, +23°C, 4mm	11	kJ/m <sup>2</sup>	ISO 180/1A
<b>ASTM Data</b>			
Tensile Modulus	4180	MPa	ASTM D 638
Tensile Strength at Yield	74	MPa	ASTM D 638
Tensile Strength at Break	73	MPa	ASTM D 638
Elongation at Yield	3.3	%	ASTM D 638
Elongation at Break	3.6	%	ASTM D 638
Flexural Modulus	4010	MPa	ASTM D 790
Izod Impact notched, 1/8 in	158	J/m	ASTM D 256
Izod Impact unnotched, 1/8 in	636	J/m	ASTM D 256

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Temp. of deflection under load, 1.80 MPa	140	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	145	°C	ISO 75-1/-2
Burning behav. at thickness h	V-1	class	IEC 60695-11-10
Thickness tested	3.0	mm	-
<b>ASTM Data</b>			
DTUL @ 66 psi	146	°C	ASTM D 648
DTUL @ 264 psi	141	°C	ASTM D 648

Other properties	Value	Unit	Test Standard
Density	1350	kg/m <sup>3</sup>	ASTM D 792

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120	°C	-
Pre-drying - Time	4	h	-
Processing humidity	≤0.02	%	-
Melt temperature	305 - 325	°C	-
Mold temperature	80 - 110	°C	-
Zone 1	295 - 305	°C	-
Zone 2	310 - 320	°C	-
Zone 3	320 - 330	°C	-
Screw speed	30 - 60	rpm	-
Back pressure	0.2 - 0.3	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Regional Availability**

North America, Europe, Asia Pacific