

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	1.8	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	25.3	MPa	ASTM D 638
Elongation at Yield	12.7	%	ASTM D 638
Izod Impact notched, 1/8 in	7.7	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	80	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Profile Extrusion, Sheet Extrusion

Special Characteristics

High impact or impact modified

Features

Copolymer, Impact Copolymer

Certifications

Drinking water contact, Drinking water contact NSF 61

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa