

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ASTM Data</b>			
Melt Flow Index, MFI	35	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ASTM Data</b>			
Tensile Strength at Yield	27.9	MPa	ASTM D 638
Elongation at Yield	14	%	ASTM D 638
Izod Impact notched, 1/8 in	63	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	73	°C	ASTM D 648
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	8	%	ASTM D 1003
<b>Other properties</b>			
Density	900	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Processing

Injection Molding

### Additives

Release agent

### Special Characteristics

Anti-static

### Features

Copolymer, Random Copolymer

### Certifications

US Pharmacopeia Class VI Approved

### Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa