

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	80	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	27.9	MPa	ASTM D 638
Elongation at Yield	14	%	ASTM D 638
Izod Impact notched, 1/8 in	53	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	74	°C	ASTM D 648
Optical properties			
ASTM Data			
Haze	8	%	ASTM D 1003
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Processing

Injection Molding

Additives

Release agent

Features

Copolymer, Random Copolymer

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa