

<b>Mechanical properties</b>	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ASTM Data</b>			
Tensile Strength	<b>41.2</b>	MPa	ASTM D 638
Elongation at Break	<b>1</b>	%	ASTM D 638
Flexural Modulus	<b>13730</b>	MPa	ASTM D 790
Flexural Strength	<b>58.9</b>	MPa	ASTM D 790
Shore D Hardness	<b>74</b>	-	ASTM D 2240
Izod Impact notched, 1/8 in	<b>29.4</b>	J/m	ASTM D 256
<b>Thermal properties</b>			
<b>ASTM Data</b>			
DTUL @ 66 psi	<b>270</b>	°C	ASTM D 648
DTUL @ 264 psi	<b>235</b>	°C	ASTM D 648
<b>Electrical properties</b>			
<b>ASTM Data</b>			
Surface Resistivity	<b>100</b>	Ohm	ASTM D 257
<b>Other properties</b>			
Density	<b>1850</b>	kg/m <sup>3</sup>	ASTM D 792

## Characteristics

### Special Characteristics

Flame retardant, Heat stabilized or stable to heat, Thermally Conductive

### Regional Availability

Europe, Asia Pacific