

AQUALOY® TR314-1

PPS-GF

LyondellBasell Industries

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Flexural modulus, 23°C	14500	MPa	ISO 178
Izod notched impact strength, +23°C	3	kJ/m ²	ISO 180/1A

Thermal properties	Value	Unit	Test Standard
ISO Data			
Temp. of deflection under load, 1.80 MPa	220	°C	ISO 75-1/-2

Other properties	Value	Unit	Test Standard
Density	1890	kg/m ³	ISO 1183

Characteristics**Regional Availability**

North America, Europe, Asia Pacific, South and Central America,
Near East/Africa