

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	15000	MPa	ISO 527
Stress at break	190	MPa	ISO 527
Strain at break	1.7	%	ISO 527
Charpy impact strength, +23°C	45	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	11	kJ/m <sup>2</sup>	ISO 179/1eA

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	280	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	260	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	23	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	35	E-6/K	ISO 11359-1/-2
Burning behav. at thickness h	V-0	class	IEC 60695-11-10
Thickness tested	0.4	mm	-

Electrical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Volume resistivity	1E14	Ohm*m	IEC 62631-3-1

Other properties	Value	Unit	Test Standard
Water absorption	0.02	%	Sim. to ISO 62
Density	1660	kg/m <sup>3</sup>	ISO 1183

Processing Recommendation Injection Molding	Value	Unit	Test Standard
Pre-drying - Temperature	120 - 140	°C	-
Pre-drying - Time	4 - 8	h	-
Processing humidity	≤0.02	%	-
Melt temperature	320 - 340	°C	-
Mold temperature	140 - 180	°C	-
Injection pressure	<1	MPa	-

**Characteristics**

**Processing**

Injection Molding

**Special Characteristics**

Heat stabilized or stable to heat

**Chemical Resistance**

General Chemical Resistance

**Applications**

Aircraft and Aerospace, Automotive, Electrical and Electronical, Encapsulation

**Regional Availability**

Europe