

RTP 1400 R-5500

PPSU

RTP Company

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	11.5	g/10min	ASTM D 1238
Temperature	365	°C	-
Load	5	kg	-
Mold Shrinkage, MD	0.006	mm/mm	ASTM D 955
Mechanical properties			
ASTM Data			
Tensile Modulus	2344	MPa	ASTM D 638
Tensile Strength	69.6	MPa	ASTM D 638
Flexural Modulus	2413	MPa	ASTM D 790
Flexural Strength	91	MPa	ASTM D 790
Izod Impact notched, 1/8 in	694	J/m	ASTM D 256
Thermal properties			
ASTM Data			
UL 94 Flame rating	V-0	-	UL 94
Thickness tested	1.59	mm	-
DTUL @ 264 psi	209	°C	ASTM D 648
Other properties			
Water Absorption, 24hr	0.37	%	ASTM D 570
Density	1290	kg/m ³	ASTM D 792
Moisture Content	0.04	%	-
Processing Recommendation Injection Molding			
Pre-drying - Temperature	149	°C	-
Pre-drying - Time	6	h	-
Melt temperature	343 - 388	°C	-

Characteristics**Processing**

Other Extrusion

Regional Availability

North America, Europe, Asia Pacific