

Product Texts

Base Polymer	Polyphenylene Sulphide
Filler/Additive System	80 % special filler
Special Features	increased thermal conductivity,electrostatically dissipating,high density
Market Segment	Automotive,Machinery,electrical and electronic
Application Area	electrical components
Typical Applications	coil formers / bobbins

Mechanical properties	Value	Unit	Test Standard
ISO Data			
^[C] Tensile Modulus	12500	MPa	ISO 527
^[C] Stress at break	45	MPa	ISO 527
^[C] Strain at break	0.4	%	ISO 527
^[C] Charpy impact strength, +23°C	7	kJ/m ²	ISO 179/1eU

[C]: CAMPUS

Thermal properties	Value	Unit	Test Standard
ISO Data			
^[C] Temp. of deflection under load, 1.80 MPa	215	°C	ISO 75-1/-2
^[C] Burning Behav. at 1.5 mm nom. thickn.	V-2	class	IEC 60695-11-10
Thickness tested	1.5	mm	-
Yellow Card available	yes	-	-

[C]: CAMPUS

Other properties	Value	Unit	Test Standard
^[C] Density	3820	kg/m ³	ISO 1183

[C]: CAMPUS

Characteristics

Processing

Injection Molding

Regional Availability

North America, Europe, Asia Pacific, Near East/Africa

Other text information

Injection molding

Pre-Drying Conditions in a dry air (dessiccant) dryer 130-140 °C
for 2-4 h
dependant on moisture content

Processing Injection Moulding melt temperature 320-340 °C
mould temperature >140 °C

Storage dry, protected from light
not above 30°C