

**Clyrell RC2472**

PP

LyondellBasell Industries

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	7	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	450	MPa	ISO 527
Yield stress	17	MPa	ISO 527
Yield strain	16	%	ISO 527
Strain at break	>50	%	ISO 527
Charpy notched impact strength, +23°C	12	kJ/m <sup>2</sup>	ISO 179/1eA

Other properties	Value	Unit	Test Standard
Density	900	kg/m <sup>3</sup>	ISO 1183

Film Properties	Value	Unit	Test Standard
<b>ASTM Data</b>			
Tensile Strength at Yield, MD	18	MPa	ASTM D 882
Tensile Strength at Break, MD	40	MPa	ASTM D 882
Elongation at Break, MD	730	%	ASTM D 882

**Characteristics****Processing**

Film Extrusion

**Applications**

Packaging

**Features**

Heat Sealable, Copolymer, Random Copolymer

**Regional Availability**

Europe

**Certifications**

Food contact, Food approval 1935/2004/EC, Food approval 10/2011, Food approval FDA 21 CFR