

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	10	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	32.3	MPa	ASTM D 638
Elongation at Yield	11	%	ASTM D 638
Rockwell Hardness	R94	-	ASTM D 785
Izod Impact notched, 1/8 in	69.4	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	82.2	°C	ASTM D 648
Other properties			
Density	900	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets

Applications

Medical

Features

Low Odor, Copolymer, Random Copolymer

Regional Availability

North America

Certifications

Medical Grade, Biocompatibility ISO 10993, US Pharmacopeia Class VI Approved