

Cosmoplene® FS5711

PP

The Polyolefin Company (Singapore) Pte Ltd

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	5.5	g/10min	ASTM D 1238

Mechanical properties	Value	Unit	Test Standard
ASTM Data			
Tensile Strength at Break	40	MPa	ASTM D 638

Thermal properties	Value	Unit	Test Standard
ASTM Data			
Melting Temperature	127	°C	ASTM D 3418

Optical properties	Value	Unit	Test Standard
ASTM Data			
Gloss	152	-	ASTM D 2457
Haze	0.2	%	ASTM D 1003

Other properties	Value	Unit	Test Standard
Density	900	kg/m ³	ASTM D 792

Film Properties	Value	Unit	Test Standard
ASTM Data			
Thickness of specimen	0.3	mm	-
Other Standards^[S]			
Tensile Modulus, MD	340	MPa	TPC Method
Tensile Modulus, TD	340	MPa	TPC Method

S: These properties are reported by the producer according standards that are different to our defaults.

Characteristics**Processing**

Film Extrusion

Special Characteristics

Transparent

Features

Heat Sealable, High Gloss

Certifications

Food contact, Food approval FDA 21 CFR

Regional Availability

Asia Pacific