

Daploy™ SF313HMS

PP

Borealis A/S

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	13	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	162	°C	ISO 11357-1/-3
Vicat softening temperature, A	148	°C	ISO 306
Other properties			
Density	900	kg/m ³	ISO 1183

Characteristics**Processing**

Coating

Certifications

Food contact

Special Characteristics

Heat stabilized or stable to heat

Regional Availability

Europe

Features

Heat Sealable, Melt Strength, Copolymer