

Daploy™ WB135HMS

PP

Borealis A/S

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	2.4	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
ISO Data			
Tensile Modulus	2000	MPa	ISO 527

Characteristics**Processing**

Other Extrusion

Features

Acoustical Barrier Properties, Foamable, Thermal Stability, Homopolymer

Certifications

Food contact

Applications

Automotive, Packaging

Regional Availability

North America, Europe, Asia Pacific, South and Central America, Near East/Africa