

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	22	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Characteristics**Processing**

Coating

Certifications

Food contact

Special Characteristics

Heat stabilized or stable to heat

Applications

Packaging

Features

Barrier Properties, Homopolymer

Regional Availability

Europe

Chemical Resistance

Grease Resistance