

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	3.1	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Tensile Modulus	1850	MPa	ISO 527
Yield stress	37	MPa	ISO 527
Yield strain	7	%	ISO 527
Strain at break	25	%	ISO 527
Charpy impact strength, +23°C	145	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	4.5	kJ/m <sup>2</sup>	ISO 179/1eA
Izod notched impact strength, +23°C	4	kJ/m <sup>2</sup>	ISO 180/1A
Ball indentation hardness	79	MPa	ISO 2039-1
<b>Thermal properties</b>			
<b>ISO Data</b>			
Melting temperature, 10°C/min	165	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	58	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	100	°C	ISO 75-1/-2
Vicat softening temperature, A	156	°C	ISO 306
Vicat softening temperature, B	94	°C	ISO 306
<b>Optical properties</b>			
<b>ASTM Data</b>			
Haze	30	%	ASTM D 1003
<b>Other properties</b>			
Density	910	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Processing

Other Extrusion, Thermoforming

### Delivery form

Pellets

### Special Characteristics

Anti-static, Transparent

### Features

Low Odor, Nucleated, Homopolymer

### Certifications

Food contact, Food approval 1935/2004/EC, Food approval FDA 21 CFR

### Applications

Packaging

### Regional Availability

Europe, Asia Pacific, Near East/Africa