

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	7.5	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Tensile Modulus	1500	MPa	ISO 527
Yield stress	35	MPa	ISO 527
Yield strain	9	%	ISO 527
Strain at break	>50	%	ISO 527
Charpy impact strength, +23°C	130	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	15	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	3.5	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	1.6	kJ/m ²	ISO 179/1eA
Ball indentation hardness	77	MPa	ISO 2039-1
Thermal properties			
ISO Data			
Melting temperature, 10°C/min	163	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	85	°C	ISO 75-1/-2
Vicat softening temperature, A	154	°C	ISO 306
Vicat softening temperature, B	90	°C	ISO 306
Optical properties			
ISO Data			
Gloss, 20°	130	-	ISO 2813
ASTM Data			
Haze	0.5	%	ASTM D 1003
Other properties			
Density	910	kg/m ³	ISO 1183

Characteristics

Processing

Other Extrusion, Thermoforming

Delivery form

Pellets

Features

Low Odor, Homopolymer

Certifications

Food contact, Food approval 1935/2004/EC, Food approval FDA 21 CFR

Applications

Monofilament

Regional Availability

Europe, Asia Pacific, Near East/Africa