

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	12	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-

Mechanical properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Tensile Modulus	1550	MPa	ISO 527
Yield stress	35	MPa	ISO 527
Yield strain	8	%	ISO 527
Strain at break	>50	%	ISO 527
Charpy impact strength, +23°C	110	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy impact strength, -30°C	15	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength, +23°C	3	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	1.5	kJ/m <sup>2</sup>	ISO 179/1eA
Ball indentation hardness	78	MPa	ISO 2039-1

Thermal properties	Value	Unit	Test Standard
<b>ISO Data</b>			
Melting temperature, 10°C/min	163	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	55	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	85	°C	ISO 75-1/-2
Vicat softening temperature, A	154	°C	ISO 306
Vicat softening temperature, B	90	°C	ISO 306

Other properties	Value	Unit	Test Standard
Density	910	kg/m <sup>3</sup>	ISO 1183

## Characteristics

### Delivery form

Pellets

### Special Characteristics

U.V. stabilized or stable to weather

### Features

Gas Fading Resistance, Low Odor, Homopolymer

### Certifications

Food contact, Food approval 1935/2004/EC, Food approval FDA 21 CFR

### Regional Availability

Europe, Asia Pacific, Near East/Africa