

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	30	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength	25.5	MPa	ASTM D 638
Elongation at Yield	8	%	ASTM D 638
Flexural Modulus	1210	MPa	ASTM D 790
Izod Impact notched, 1/8 in	110	J/m	ASTM D 256
Thermal properties			
ASTM Data			
DTUL @ 66 psi	71.1	°C	ASTM D 648
Other properties			
Density	938	kg/m ³	ASTM D 792

Characteristics

Delivery form

Pellets, Black

Features

Copolymer

Certifications

Recycled Resin Content

Regional Availability

North America