

| Processing/Physical Characteristics | Value | Unit | Test Standard |
|--------------------------------------|-------|-------------------|---------------|
| ASTM Data | | | |
| Melt Flow Index, MFI | 10 | g/10min | ASTM D 1238 |
| Temperature | 230 | °C | - |
| Load | 2.16 | kg | - |
| Mechanical properties | | | |
| ASTM Data | | | |
| Tensile Strength at Yield | 27 | MPa | ASTM D 638 |
| Tensile Strength at Break | 18 | MPa | ASTM D 638 |
| Flexural Modulus | 1373 | MPa | ASTM D 790 |
| Rockwell Hardness | R 80 | - | ASTM D 785 |
| Izod Impact notched, 1/8 in | 108 | J/m | ASTM D 256 |
| Izod Impact notched, Low-Temperature | 39 | J/m | ASTM D 256 |
| Temperature | -20 | °C | - |
| Thermal properties | | | |
| ASTM Data | | | |
| DTUL @ 66 psi | 110 | °C | ASTM D 648 |
| Vicat Temperature | 150 | °C | ASTM D 1525 |
| Other properties | | | |
| Density | 910 | kg/m ³ | ASTM D 792 |

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Special Characteristics

Anti-static, High impact or impact modified, U.V. stabilized or stable to weather

Features

Copolymer, Impact Copolymer

Certifications

Food contact, Food approval FDA 21 CFR

Applications

Automotive, Electrical and Electronical

Regional Availability

Asia Pacific