

Processing/Physical Characteristics	Value	Unit	Test Standard
ASTM Data			
Melt Flow Index, MFI	25	g/10min	ASTM D 1238
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ASTM Data			
Tensile Strength at Yield	25	MPa	ASTM D 638
Tensile Strength at Break	16	MPa	ASTM D 638
Elongation at Break	357	%	ASTM D 638
Flexural Modulus	885	MPa	ASTM D 790
Thermal properties			
ASTM Data			
Melting Temperature	146	°C	ASTM D 3418
Other properties			
Density	910	kg/m ³	ASTM D 792

Characteristics

Processing

Other Extrusion, Coating

Features

Good Adhesion, Copolymer, Random Copolymer

Delivery form

Pellets

Regional Availability

Asia Pacific