

Processing/Physical Characteristics	Value	Unit	Test Standard
<b>ISO Data</b>			
Melt flow index, MFI	1.8	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
<b>Mechanical properties</b>			
<b>ISO Data</b>			
Yield stress	26	MPa	ISO 527
Flexural modulus, 23°C	900	MPa	ISO 178
<b>Thermal properties</b>			
<b>ISO Data</b>			
Vicat softening temperature, A	130	°C	ISO 306

### Characteristics

#### Processing

Injection Molding, Blow Molding

#### Delivery form

Pellets

#### Special Characteristics

Sterilizable, Steam sterilization

#### Features

Copolymer, Random Copolymer

#### Certifications

Medical Grade, US Pharmacopeia Class VI Approved

#### Applications

Medical

#### Regional Availability

Europe