

Processing/Physical Characteristics	Value	Unit	Test Standard
ISO Data			
Melt flow index, MFI	23	g/10min	ISO 1133
Temperature	230	°C	-
Load	2.16	kg	-
Mechanical properties			
ISO Data			
Yield stress	26	MPa	ISO 527
Flexural modulus, 23°C	980	MPa	ISO 178
Thermal properties			
ASTM Data			
Melting Temperature	146	°C	ASTM D 3418

Characteristics

Processing

Injection Molding

Delivery form

Pellets

Additives

Lubricants, Antiblocking agent

Special Characteristics

Transparent

Features

Copolymer, Random Copolymer

Certifications

Medical Grade, US Pharmacopeia Class VI Approved

Applications

Medical

Regional Availability

Europe